

TECHNICAL LEAFLET

Cleaning and care instructions

EGGER PerfectSense lacquered boards


Material description:

Decorative, UV coated wood-based material.

Core board version as EGGER MDF ST E1

Use:

Decorative wood-based panels for indoor use.



PERFECTSENSE LACQUERED BOARDS – PRODUCT DESCRIPTION

PerfectSense is a new premium category of high-gloss and matt decorative lacquered boards, using tried and tested EGGER MDF quality as a base, which is used in high-end furniture and interior design application. The revolutionary UV-lacquered coating process means all décors in the EGGER matching decor collection can be supplied as PerfectSense Matt, with no-fingerprint properties, or PerfectSense Gloss with its smooth surface and relief effect.

APPLICATION

The following information should be observed for daily use:

- Spilled liquids should always be wiped or cleaned up immediately, as prolonged exposure to some substances may have a negative effect on the PerfectSense surface properties (see table 1).
- Particularly in the areas around cut-outs and joints, spilled liquids should always be cleaned up quickly and thoroughly.
- As a general rule dirt and spilled substances such as tea, coffee, wine etc. should be cleaned immediately as the cleaning work increases if they are left to dry.
- For best results, always wipe the surface dry with a regular soft cloth after damp cleaning.

LIGHT, FRESH SOILING

Use a soft, lint-free cloth, a leather chamois or a sponge. Do not use **microfibre cloths or cleaning erasers**, since these often contain fine abrasive particles which can lead to scratching of the surface. Wipe the damp surface dry using absorbent paper towel (e.g. kitchen roll) to prevent the formation of streaks.

Streaks often form when the surface is cleaned with organic solvents, together with cold water and old cloths or window leathers. With all cleaning methods, to prevent shadings or streaks, we recommend wiping with warm water and then drying the surface using normal paper towels or cotton cloths.

NORMAL SOILING – LONGER REACTION TIME

With this type of soiling, clean the surface with warm water using a clean cloth, soft sponge or soft brush. If required, a light-duty household cleaning agent or neutral soap without abrasive ingredients can be used. Wipe with pure water to remove any residual cleaning agent and to avoid the formation of streaks. Then dry the surface with a clean, absorbent cloth or paper towel. Standing water and other liquids can cause permanent damage.

For stubborn dirt (aged grease residues, shoe polish, felt pen etc.), a regular glass cleaner can be used. Always test cleaning agents first on a small inconspicuous area.

THE FOLLOWING CLEANING AGENTS MUST NOT BE USED:

- Scouring and abrasive agents (e.g. microfibre cloths, abrasive powders, scouring pads, steel wool).
- Polish, washing powder, furniture cleaner, bleach.
- Cleaning agents with strong acids and strong acid salts, harsh chemical substances or solvents (e.g. alcohol, ammonia).
- Steam cleaning machines.

PerfectSense lacquered boards have a very high resistance to the most commonly used chemicals (stress group 1 B). These are listed in Table 1 and have been tested according to BS EN 12720:2009-07.

Table 1: Surface testing according to BS EN 12720:2009-07

| Testing agent | Exposure time | Result |
|------------------------|---------------|--------|
| 1 Acetic acid | 1 h | 5 |
| 2 Citric acid | 1 h | 5 |
| 3 Ammonia water | 2 min | 5 |
| 4 Ethyl alcohol | 1 h | 5 |
| 5 Red wine | 6 h | 5 |
| 6 Beer | 6 h | 5 |
| 7 Cola | 16 h | 5 |
| 8 Coffee | 16 h | 5 |
| 9 Black tea | 16 h | 5 |
| 10 Blackcurrant juice | 16 h | 5 |
| 11 Condensed milk | 16 h | 5 |
| 12 Water | 16 h | 5 |
| 13 Petrol | 2 min | 5 |
| 14 Acetone | 10 s | 5 |
| 15 Ethyl butyl acetate | 10 s | 5 |
| 16 Butter | 16 h | 5 |
| 17 Olive oil | 16 h | 5 |
| 18 Mustard | 6 h | 5 |
| 19 Onion | 6 h | 5 |
| 20 Disinfectant | 10 min | 5 |
| 21 Cleaning agent | 1 h | 5 |
| 22 Cleaning solution | 1 h | 5 |

Table 2 Descriptive numerical rating code

| Numerical rating | Description |
|------------------|---|
| 5 | No change Test area indistinguishable from adjacent surrounding area. |
| 4 | Minor change Test area distinguishable from adjacent surrounding area, only when the light source is mirrored on the test surface and is reflected towards the observer's eye, e. g. discolouration, change in gloss and colour. No change in the surface structure, e.g. swelling, fibre raising, cracking, blistering. |
| 3 | Moderate change Test area distinguishable from adjacent surrounding area, visible in several viewing directions, e. g. discolouration, change in gloss and colour. No change in the surface structure, e.g. swelling, fibre raising, cracking, blistering. |
| 2 | Significant change Test area clearly distinguishable from adjacent surrounding area, visible in all viewing directions, e. g. discolouration, change in gloss and colour, and/or structure of the surface slightly changed, e.g. swelling, fibre raising, cracking, blistering. |
| 1 | Strong change The structure of the surface being distinctly changed and/or discolouration, change in gloss and colour, and/or the surface material being totally or partially removed, and/or the filter paper adhering to the surface. |

GENERAL INFORMATION

These recommendations apply equally to PerfectSense Matt (PM) and Gloss (PG) surfaces, which have a distinctive look and feel. In combination with dark uni colours and dark woodgrain decors, it is important to note that signs of everyday wear and tear will be more visible than with light decors. The actual effect of PerfectSense is just as strong with light decors, but the visual impact is greater with dark decors. When the effects of wear and tear become visible, this does not actually represent any compromise in terms of surface quality. PerfectSense lacquered boards satisfy the high requirements of the AMK (Arbeitsgemeinschaft Die Moderne Küche e.V.) and the associated European standards with respect to all relevant quality requirements. For uses and application areas, quality requirements, technical data and supply formats, please see the respective data sheets.

FURTHER DOCUMENTS

PerfectSense Lacquered Boards Technical Data Sheet
 PerfectSense Lacquered Boards Processing Instructions

Provisional note:

This technical data sheet has been carefully drawn up to the best of our knowledge. We accept no liability for any mistakes, errors in standards or printing errors. In addition, technical modifications may result from the continuous development of PerfectSense lacquered boards, as well as from changes to standards and public law documents. The contents of this technical data sheet should therefore not be considered as instructions for use or as legally binding.